

K-88 Admix

**100% acrylic admixture
for cementitious materials.
Improve strength,
durability, bond
and curing.**

WHERE TO USE
**Structural Skin,
Conpro Stucco, Foundation Coat,
Conpro Seal, Plastermix,
Conpro One Shot 2C, and mortar.**

PERFORMANCE CHARACTERISTICS

Promotes curing

- Reduces need to moist cure materials in conditions up to 85°F. Reduces shrinkage induced cracking.

Increases bond

- Promotes chemical adhesion to substrate.

Durability

- Increases compressive and tensile strengths. Increases freeze/thaw resistance.

Water resistance

- Increases density and improves resistance to water entry.

SURFACE PREPARATION

- *K-88 Admix* is an admixture. Refer to the specific product bulletin for material to be used.

PRIMING

- Follow the instructions of the material to which *K-88 Admix* will be added.

MIXING

- Stir or shake container gently and pour into mix at the desired addition rate.

APPLICATION

- *Structural Skin*
1 quart/50 lbs. bag
for curing.
2 quarts/50 lbs. bag
for Exterior Wall Systems.
- *Conpro Stucco*
1 quart/50 lbs. bag.
- *Plastermix*
1 quart/50 lbs. bag.
- *Conpro One Shot 2C*
1 gallon/50 lbs. bag.
- Field mix stucco
1 part *K-88 Admix* to 2 parts water.
- Cement parge coat
1 part *K-88 Admix* to 2 parts water.
- Mortar and concrete
1 part *K-88 Admix* to 2 parts water.

CURING

- Follow the instructions of the Conproco product to which *K-88 Admix* is added.

CLEAN UP

- Clean tools and equipment with water.

K-88 Admix

COVERAGE/YIELD

- Refer to *Application*

PRODUCT HANDLING

Packaging

- Quart, 1, 5 and 55 gallon containers.

Shelf Life

- 18 months in unopened containers.

Storage

- Protect from freezing.
- Transport and store in cool, clean, dry conditions in unopened containers.
- High temperature will reduce shelf life.

LIMITATIONS

- Do not apply if temperature of substrate is below 45°F.
- Do not apply if ambient temperature is below 45°F.
- Do not re-temper mixes modified with *K-88 Admix*.

HEALTH AND SAFETY

- Do not ingest.
- Avoid contact with skin and eyes.
- Avoid breathing vapors.
- Refer to Material Safety Data Sheet (MSDS) for additional information.

FIRST AID

- In case of skin contact, wash thoroughly with soap and water. For eye contact, flush immediately with a high volume of water for at least 15 minutes and contact a medical professional. For respiratory problems, remove person to fresh air. If respiratory difficulty persists, contact a medical professional.

DISPOSAL

- Dispose of material in accordance with local, state or federal regulations.

TECHNICAL DATA

Physical state and appearance		Milky liquid		
Base		Aqueous		
Polymer		100% acrylic		
Odor		Ammoniacal		
pH		>8		
Percent solids by weight		27%		
Density of liquid coatings	ASTM D1475	8.4 lbs./gal.		
Results typical for 3/4 - 3 inch mix		7 Days	14 Days	28 Days
Compressive strength	ASTM C109			
Design mix without K-88 Admix – psi		2725	3375	3725
Design mix with K-88 Admix – psi		3400	4150	4700
Percent increase – %		25	23	26
Tensile strength	ASTM C307			
Design mix without K-88 Admix – psi		95	360	360
Design mix with K-88 Admix – psi		385	390	400
Percent increase – %		30	8	11

FOR PROFESSIONAL USE ONLY

Conproco Corp. warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current technical data sheet if used as directed within shelf life. User determines suitability of product for use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor. March 2010.

NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. CONPROCO CORP. SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES.

conproco[®]
CORPORATION

17 PRODUCTION DRIVE, DOVER, NEW HAMPSHIRE 03820
TELEPHONE 800.258.3500 • FAX 603.743.5744 • WEB ADDRESS www.conproco.com