

Color K-88 Admix

**100% acrylic admixture
for cementitious materials,
formulated to provide color.**

WHERE TO USE
White Conpro Stucco,
to obtain Masonry Series Colors, refer to
Conproco Product & Color Selection Guide*.

Performance Characteristics

Colorfast

- Provides excellent dispersion of color through mix.

Color choices

- Choose from 14 natural earth tone colors.

Promotes curing

- Reduces need to moist cure materials in most cases. Reduces shrinkage induced cracking.

Increases bond

- Promotes chemical adhesion to substrate.

Durability

- Increases compressive and tensile strengths. Increases freeze/thaw resistance.

Water resistance

- Increases density and improves resistance to water entry.

* Color K-88 Admix can be used with Conproco products Structural Skin, Plastermix, and ProMasonry Decor Seal, to achieve colors similar, but not identical to Conpro Stucco.

Surface Preparation

- K-88 Admix is an admixture. Refer to the specific product bulletin for material to be used for surface preparation.

Priming

- Follow the instructions of the material to which Color K-88 Admix will be added.

Mixing

- Stir or vigorously shake container and pour complete contents into mix. Ensure that all of the liquid and pigment are emptied from container.

Curing

- Follow the instructions of the Conproco product to which Color K-88 Admix is added.

Clean Up

- Clean tools and equipment with water.

Color K-88 Admix

Coverage/Yield

- 1 quart per 50 lbs. bag of Conproco Stucco.

Product Handling

Packaging

- Quart containers.

Shelf Life

- 18 months in unopened containers.

Storage

- Protect from freezing.
- Transport and store in cool, clean, dry conditions in unopened containers.
- High temperature will reduce shelf life.

Limitations

- Do not apply if temperature of substrate is below 45°F.
- Do not apply if ambient temperature is below 45°F.
- Do not re-temper mixes modified with Color K-88 Admix.

Health and Safety

- Do not ingest
- Avoid contact with skin and eyes.
- Avoid breathing vapors.
- Refer to Safety Data Sheet (SDS) for additional information.

First Aid

- In case of skin contact, wash thoroughly with soap and water.
- For eye contact, flush immediately with a high volume of water for at least 15 minutes and contact a medical professional.
- For respiratory problems, remove person to fresh air.
- If respiratory difficulty persists, contact a medical professional.

Disposal

- Dispose of material in accordance with local, state and federal regulations.

Technical Data

Physical state and appearance		Colored liquid		
Base		Aqueous		
Polymer		100% acrylic		
Odor		Ammoniacal		
pH		>9.5		
Percent solids by weight	Wet mix	45 - 65% by weight dependent on color		
Density of liquid coatings	ASTM D1475	8.4 lbs./gal.		
		7 Days	14 Days	28 Days
Compressive strength		ASTM C109		
Design mix without Color K-88 Admix – psi		2725	3375	3725
Design mix with Color K-88 Admix – psi		3400	4150	4700
Percent increase - %		25	23	26
Tensile strength		ASTM C307		
Design mix without Color K-88 Admix – psi		95	360	360
Design mix with Color K-88 Admix – psi		385	390	400
Percent increase - %		30	8	11

FOR PROFESSIONAL USE ONLY

Conproco warrants this product for one year from the date of manufacture to be free from manufacturing defects and to meet the technical properties on the current technical data sheet if used as directed within shelf life. User determines suitability of product for use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product, exclusive of labor or cost of labor. January 7, 2016.

NO OTHER WARRANTIES EXPRESSED OR IMPLIED SHALL APPLY, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. CONPROCO CORP SHALL NOT BE LIABLE UPON ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES.

conproco®

17 PRODUCTION DRIVE, DOVER, NH 03820
TELEPHONE 800.258.3500 • FAX 603.743.5744 • WEB ADDRESS www.conproco.com