

K-88 Admix

100% acrylic admixture for cementitious materials. Improve strength, durability, bond and curing.

WHERE TO USE

Structural Skin®, Conpro Stucco, Foundation Coat, ProMasonry Decor Seal, Plastermix, and mortar.

Performance Characteristics

Promotes curing

- Reduces need to moist cure materials in conditions up to 85°F. Reduces shrinkage induced cracking.

Increases bond

- Promotes chemical adhesion to substrate.

Durability

- Increases compressive and tensile strengths. Increases freeze/thaw resistance.

Water resistance

- Increases density and improves resistance to water entry.

Surface Preparation

- K-88 Admix is an admixture. Refer to the specific product bulletin for material to be used.

Priming

- Follow the instructions of the material to which K-88 Admix will be added.

Mixing

- Stir or shake container gently and pour into mix at the desired addition rate.

Application

- Structural Skin®
1 quart/50 lbs. bag
for curing.
- 2 quarts/50 lbs. bag
for Exterior Wall Systems.
- Conpro Stucco
1 quart/50 lbs. bag.
- Plastermix
1 quart/50 lbs. bag.
- Field mix stucco
1 part K-88 Admix to 2 parts water.
- Cement parge coat
1 part K-88 Admix to 2 parts water.
- Mortar and concrete
1 part K-88 Admix to 2 parts water.

Curing

- Follow the instructions of the Conproco product to which K-88 Admix is added.

Clean Up

- Clean tools and equipment with water.

K-88 Admix

Coverage/Yield

- Refer to Application

Product Handling

Packaging

- Quart, 1, 5 and 55 gallon containers.

Shelf Life

- 18 months in unopened containers.

Storage

- Protect from freezing.
- Transport and store in cool, clean, dry conditions in unopened containers.
- High temperature will reduce shelf life.

Limitations

- Do not apply if temperature of substrate is below 45°F.
- Do not apply if ambient temperature is below 45°F.
- Do not re-temper mixes modified with K-88 Admix.

Health and Safety

- Product is alkaline.
- Avoid contact with skin and eyes.
- Avoid breathing vapors.
- Refer to Safety Data Sheet (SDS) for additional information.

First Aid

- In case of skin contact, wash thoroughly with soap and water.
- For eye contact, flush immediately with a high volume of water for at least 15 minutes and contact a medical professional.
- For respiratory problems, remove person to fresh air.
- If respiratory difficulty persists, contact a medical professional.

Disposal

- Dispose of material in accordance with local, state and federal regulations.

Technical Data

Physical state and appearance		Milky liquid
Base		Aqueous
Polymer		100% acrylic
Odor		Ammoniacal
pH		>8
Percent solids by weight		27%
Density of liquid coatings	ASTM D1475	8.4 lbs./gal.
Results typical for 3/4 -3 inch mix		7 Days 14 Days 28 Days
Compressive strength	ASTM C109	
Design mix without K-88 Admix – psi		2725 3375 3725
Design mix with K-88 Admix – psi		3400 4150 4700
Percent increase - %		25 23 26
Tensile strength	ASTM C307	
Design mix without K-88 Admix – psi		95 360 360
Design mix with K-88 Admix – psi		385 390 400
Percent increase - %		30 8 11

FOR PROFESSIONAL USE ONLY

Conproco warrants this product for one year from the date of manufacture to be free from manufacturing defects and to meet the technical properties on the current technical data sheet if used as directed within shelf life. User determines suitability of product for use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product, exclusive of labor or cost of labor. August 23, 2018.

NO OTHER WARRANTIES EXPRESSED OR IMPLIED SHALL APPLY, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. CONPROCO CORP SHALL NOT BE LIABLE UPON ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES.

conproco®

17 PRODUCTION DRIVE, DOVER, NH 03820
TELEPHONE 800.258.3500 • FAX 603.743.5744 • WEB ADDRESS www.conproco.com