

Quick Shot

Single component, fast setting, high build, low shrinkage, cementitious repair mortar. Add K-88 Admix for polymer modified repair mortar.

WHERE TO USE

Fast repairs to vertical, overhead and horizontal concrete, above or below grade.

Performance Characteristics

Fast setting

- Formulated to set quickly to increase productivity.

High build

- Superior hang for overhead vertical applications.

Low shrinkage

- Maintains integrity of repair, resists cracking.

Thermal compatibility

- Prevents delamination due to temperature change.

Durable

- Resistant to weathering action, excellent freeze/thaw stability and abrasion resistance.

Very low permeability

- Resistant to deicing salts, carbonation, chloride, and chemical attack.

Single component

- Easy to batch in less than full bag quantities.

Surface Preparation

- Remove loose and deteriorated material, laitance, dirt, dust, oil and any surface contaminants that will inhibit proper bond.
- Saw cut edges with a diamond blade at a 90° angle to eliminate feather edging. Avoid polishing the edges as this will inhibit bond.
- Avoid bruising or micro cracking during surface preparation. Refer to ICRI Surface Preparation Guide 03732.
- Repair zone must be a minimum of 1/2 inch deep, of simple geometry, with no complex edge conditions.
- Avoid long narrow repairs; these have a tendency to crack.

- Saturate substrate with clean water, (saturated surface dry/SSD), with no standing water during *Priming or Application*.
- Remove concrete from corroded steel and several inches beyond to expose non-corroded steel.
- Provide a 3/4 inch clearance between the concrete and steel.
- Damaged reinforcing steel should be inspected by a qualified engineer and appropriate action taken.

Priming

Concrete

- Prime the prepared substrate including all edges with a slurry coat of the repair mortar. Work the slurry into the substrate to ensure intimate contact and establish bond. The repair material must be applied while slurry is wet. If the slurry dries, remove and recoat.
- Alternatively, use Conpro Primer or ECB as a bonding primer. Refer to the individual product technical data bulletin for information.

Reinforcing Steel

- Remove all scaling rust from reinforcing steel.
- Apply ECB anti-corrosion coating.

Mixing

- Mix only as much material as can be placed in 10-15 minutes.
- Mechanically mix using a low speed drill (400-600 rpm) and mixing paddle or mortar mixer.
- Pour slightly less than 1 gallon of potable water into a clean mixing vessel and slowly add all 50 lbs. of material.
- Substitute 1 quart of K-88 Admix for water for a polymer modified repair mortar.
- Mix continuously for 3 minutes to a uniform, lump-free consistency.

- Add up to 1 cup of additional water if needed.
- Do not overmix, as this will entrain excess air.

Application

- At the time of application, surfaces should be saturated surface dry (SSD) but hold no standing water.
- Follow instructions for Priming.
- Force the material against the edges of the repair, working toward the center.
- Material may be applied in multiple lifts of not less than 3/8 inch and up to 4 inches.
- Consolidate each lift and allow to stiffen to thumb-print hard before continuing.
- Scratch (cross-hatch) each lift to prepare surface for subsequent lift.
- Finish with a sponge float or trowel.
- Do not overwork the finish.
- For horizontal or supported applications over 2 inches, a maximum of 30 lbs of 3/8 inch aggregate per 50 lb bag may be added to reduce shrinkage and improve yield. Aggregate must be non-reactive, low absorption, graded and high density.

Curing

- Dampen the repair with a fine mist of water for 24 hours or moist cure with wet burlap and polyethylene.
- Protect repair from direct sunlight, wind, rain and frost during curing period.

Clean Up

- Clean tools and equipment with water immediately after use.
- Cured material must be removed mechanically.

Quick Shot

Coverage/Yield

- 0.44 ft³/50 lbs.
- 0.67 ft.³ when extended with 30 lbs. of 3/8 inch aggregate.

Product Handling

Packaging

- 50 lbs. multi-wall, poly lined bags.

Shelf Life

- Bag - 12 months when properly stored.

Storage

- Transport and store in cool, clean, dry conditions in unopened containers.
- High temperature or high humidity will reduce shelf life.

Limitations

- Do not apply unless substrate and ambient temperature can be maintained at a minimum of 40°F for 24 hours. Refer to ACI Cold Weather Application Guidelines.

- Cold mixing water and low temperature will retard set. Hot water and high temperature will accelerate set.
- Protect application from precipitation and high wind for at least 8 hours.
- Do not add more water than specified, this will lower strengths and cause shrinkage cracking.
- Avoid overworking material during placement and finishing - this will produce surface (map) cracking.
- Surface whitening can occur when polyethylene is in contact with the material during the first 24 hours of curing.

Health and Safety

- Product is alkaline.
- Do not ingest.
- Avoid breathing dust.
- Avoid contact with skin and eyes.
- Refer to Safety Data Sheet (SDS) for additional information.

First Aid

- In case of skin contact, wash thoroughly with soap and water.
- For eye contact, flush immediately with a high volume of water for at least 15 minutes and contact a medical professional.
- For respiratory problems, remove person to fresh air.

Disposal

- Dispose of material in accordance with local, state and federal regulations.

Technical Data

| | | | | | | |
|-----------------------------------|-----------|-----------------------|---|--------------|---------------|----------------|
| Physical state and appearance | | | Fine, gray powder | | | |
| Base | | | Portland cement | | | |
| Water/cement ratio | | | 0.45 | | | |
| Vicat @ 73°F under lab conditions | | | Initial – 9-15 minutes Final – 16-25 minutes | | | |
| | | | 4 Hrs | 1 Day | 7 Days | 28 Days |
| Compressive strength – psi | ASTM C109 | Quick Shot | 700 | 2500 | 3100 | 5400 |
| | ASTM C39 | Quick Shot extended* | 500 | 2100 | 3100 | 4000 |
| | ASTM C109 | K-88 Admix modified** | 400 | 2500 | 3900 | 5300 |
| Tensile strength – psi | ASTM C307 | Quick Shot | | | 300 | 500 |
| | ASTM C307 | K-88 Admix modified** | | | 300 | 700 |
| Flexural strength - psi | ASTM C348 | Quick Shot | | | 600 | 900 |

* Extended with 30 lbs. of 3/8 inch aggregate per bag. ** Modified with 1 quart of K-88 Admix per bag. *** Both aggregate and K-88 Admix added per bag.

FOR PROFESSIONAL USE ONLY

Conproco warrants this product for one year from the date of manufacture to be free from manufacturing defects and to meet the technical properties on the current technical data sheet if used as directed within shelf life. User determines suitability of product for use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product, exclusive of labor or cost of labor. January 8, 2016.

NO OTHER WARRANTIES EXPRESSED OR IMPLIED SHALL APPLY, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. CONPROCO CORP SHALL NOT BE LIABLE UPON ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES.

conproco[®]

17 PRODUCTION DRIVE, DOVER, NH 03820
TELEPHONE 800.258.3500 • FAX 603.743.5744 • WEB ADDRESS www.conproco.com