

Conpro One Shot

Trowel applied, single component, polymer modified, Portland cement material for horizontal applications up to 1/2 inch. Can be extended with 3/8 inch aggregate.

WHERE TO USE
Resurface balconies, parking decks, industrial floors, loading docks and ramps.

Performance Characteristics

Low shrinkage

- n Maintains integrity of repair, resists cracking.

Thermal compatibility

- n Prevents delamination due to temperature change.

Durable

- n Resistant to weathering action, excellent freeze/thaw stability and abrasion resistance.

Very low permeability

- n Resistant to deicing salts, carbonation, chloride, and chemical attack.

Dimensionally stable

- n Ideal for large areas.

Abrasion resistant

- n Hard, durable surface for long term wear.

High early strength

- n Open to foot traffic in 24 hours, pneumatic tire in 72 hours.

Surface Preparation

- n Remove loose and deteriorated material, laitance, dirt, dust, oil and any surface contaminants that will inhibit proper bond.
- n Saw cut edges with a diamond blade at a 90° angle to eliminate feather edging. Avoid polishing the edges as this will inhibit bond.
- n Remove a minimum 1/16 inch of surface (CSP 5) by abrasive blasting, steel shotblasting, scarifying, needle-scaling or high pressure water.
- n Avoid bruising or micro cracking during surface preparation. Refer to ICRI Surface Preparation Guide 03732.
- n Repair zone must be a minimum of 1/8 inch deep, of simple geometry, with no complex edge conditions.
- n Avoid long narrow repairs; these have a tendency to crack.
- n Apply [Conpro Start](#) where consolidant is of benefit.

- n Saturate substrate with clean water, (saturated surface dry/SSD), with no standing water during [Priming](#) or [Application](#).
- n Remove concrete from corroded steel and several inches beyond to expose non-corroded steel.
- n Provide a 3/4 inch clearance between the concrete and steel.
- n Damaged reinforcing steel should be inspected by a qualified engineer and appropriate action taken.

Priming

Concrete

- n Use [Conpro Primer](#), as a bonding primer. Refer to the individual product technical data bulletin for information.
- n Alternatively, prime the prepared substrate including all edges with a slurry coat of the repair mortar. Work the slurry into the substrate to ensure intimate contact and establish bond. The repair material must be applied while slurry is wet. If the slurry dries, remove and recoat.

Reinforcing Steel

- n Remove all scaling rust from reinforcing steel.
- n Apply [ECB](#) anti-corrosion coating.

Mixing

- n Mechanically mix using a low speed drill (400-600 rpm) and mixing paddle or mortar mixer.
- n Pour 3 quarts of potable water into a clean mixing vessel and slowly add all of the powder.
- n Mix continuously for 3 minutes to a uniform, lump-free consistency.
- n Add up to 1 pint of additional water, if needed.
- n Allow to "breathe" for 1 minute and remix for 1 minute. This will improve workability and open time.
- n Do not overmix, as this will entrain excess air.

Application

- n At the time of application, surfaces should be saturated surface dry (SSD) but hold no standing water.
- n Follow instructions for [Priming](#).
- n Trowel in key coat.
- n Double back applying material necessary to complete application.
- n Apply with a motion similar to placing concrete.
- n Form applications must be consolidated with vibrator.
- n Finish with a magnesium float or trowel.
- n Do not overwork the finish.
- n For applications over 1/2 inch, add up to 30 lbs. of 3/8 inch aggregate. Aggregate must be non-reactive, low absorption, graded and high density.

Curing

- n Dampen the repair with a fine mist of water for 24 hours or moist cure with wet burlap and polyethylene. Alternatively, apply [ProMasonry Cure & Seal](#).
- n Protect repair from direct sunlight, wind, rain and frost during curing period.

Clean Up

- n Clean tools and equipment with water immediately after use.
- n Cured material must be removed mechanically.

Conpro One Shot

Coverage/Yield

- n 0.42 ft³/50 lbs.
- n 0.65 ft.³ when extended with 30 lbs. of 3/8 inch aggregate.

Product Handling

Packaging

- n 50 lbs. paper bags.

Shelf Life

- n 12 months when properly stored.

Storage

- n Transport and store in cool, clean, dry conditions in unopened containers.
- n High temperature or high humidity will reduce shelf life.

Limitations

- n Do not apply unless substrate and ambient temperature can be maintained at a minimum of 40°F for 24 hours. Refer to ACI Cold Weather Application Guidelines.

- n Cold mixing water and low temperature will retard set. Hot water and high temperature will accelerate set.
- n Protect application from precipitation and high wind for at least 8 hours.
- n Do not mix more material than can be placed in 30 minutes.
- n Do not re-temper, this will damage the cross-linking of the polymer and cause cracking and loss of bond.
- n Do not add more water than specified - this will lower strengths and cause shrinkage cracking.
- n Avoid overworking material during placement and finishing - this will produce surface (map) cracking.

Health and Safety

- n Product is alkaline.
- n Do not ingest.
- n Avoid breathing dust.

- n Avoid contact with skin and eyes.
- n Refer to Safety Data Sheet (SDS) for additional information.

First Aid

- n In case of skin contact, wash thoroughly with soap and water.
- n In case of eye contact, flush with a high volume of water for at least 15 minutes and contact a medical professional.
- n For respiratory problems, remove person to fresh air.

Disposal

- n Dispose of material in accordance with local, state and federal regulations.

Technical Data

Physical state and appearance		Fine, gray powder
Base		Portland cement
pH	Wet mix	>12
Aggregate type		Sharp quartz silica
Water/cement ratio		0.48*
Density	Wet mix	110 lbs./ft. ³
Setting time by vicat needle	ASTM C191	Initial 200 minutes – Final 245 minutes
Percent air by volumetric	ASTM C173	6%
Resistance to deicing chemicals under freeze/thaw	ASTM C672	50 cycles – 0 rating – no effect
Length change	ASTM C157	< 1000 µstrains @ 28 days – air cure < 500 µstrains @ 28 days – wet cure
Slant shear bond strength - epoxy	ASTM C882	1500 psi – without slurry coat 2000 psi – with slurry coat
		1 Day 7 Days 14 Days 28 Days
Compressive strength – psi	ASTM C109	1740 4500 5000
Flexural strength – 3 point loading - psi	ASTM C78	1010
Tensile strength – psi	ASTM C307	600 640 740

*Test run using 3 quarts water per 50 lbs. bag of Conpro One Shot.

FOR PROFESSIONAL USE ONLY

Conproco warrants this product for one year from the date of manufacture to be free from manufacturing defects and to meet the technical properties on the current technical data sheet if used as directed within shelf life. User determines suitability of product for use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product, exclusive of labor or cost of labor. January 8, 2016.

NO OTHER WARRANTIES EXPRESSED OR IMPLIED SHALL APPLY, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. CONPROCO CORP SHALL NOT BE LIABLE UPON ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES.

conproco[®]

17 PRODUCTION DRIVE, DOVER, NH 03820
TELEPHONE 800.258.3500 • FAX 603.743.5744 • WEB ADDRESS www.conproco.com